

# BONA® DRIFAST™ STAIN



*Bona DriFast Stain is a revolutionary, oil-modified quick drying stain that penetrates, stains, and seals bare wood. It is a premium, fast-drying stain that is compatible with all Bona waterborne and oil-modified finish systems. It is available in 14 beautiful wood tones and white and can be blended for an endless color palette.*



# Bona® Drifast™ Stain Cross Reference Chart for Minwax® Wood Finish™ Stain

*Note: All matches were made using red oak that had a final screen cut of 80 grit. These blends should be used only as a starting point and further adjustments may be necessary to achieve the desired end result.*

MANUFACTURER	TYPE	NAME	BONA BLEND (DriFast Stain)
Minwax	Minwax® Wood Finish™ Stain	Natural 209	Natural
Minwax	Minwax® Wood Finish™ Stain	Golden Oak 210B	Golden Oak
Minwax	Minwax® Wood Finish™ Stain	Ebony 2718	Ebony
Minwax	Minwax® Wood Finish™ Stain	Jacobean 2750	Jacobean
Minwax	Minwax® Wood Finish™ Stain	Early American 230	Early American
Minwax	Minwax® Wood Finish™ Stain	Special Walnut 224	Special Walnut
Minwax	Minwax® Wood Finish™ Stain	Red Mahogany 225	Red Mahogany
Minwax	Minwax® Wood Finish™ Stain	Provincial 211	Provincial
Minwax	Minwax® Wood Finish™ Stain	Golden Pecan 245	5 Natural: 2 Golden: 0.5 Rosewood
Minwax	Minwax® Wood Finish™ Stain	Cherry 235	5 Natural: 1 Golden: 1 Rosewood
Minwax	Minwax® Wood Finish™ Stain	Puritan Pine 218	5 Natural: 1 Golden: 0.25 Rosewood
Minwax	Minwax® Wood Finish™ Stain	English Chestnut 233	4 Special Walnut: 1 Red Mahogany
Minwax	Minwax® Wood Finish™ Stain	Colonial Maple 223	3 Natural: 1 Rosewood: 1 Golden: .25 White
Minwax	Minwax® Wood Finish™ Stain	Dark Walnut 2716	3 Jacobean: 1 Provincial
Minwax	Minwax® Wood Finish™ Stain	Ipswitch Pine 221	2 Natural: 1 Golden: 1.5 Rosewood
Minwax	Minwax® Wood Finish™ Stain	Sedona Red 222	No Blend
Minwax	Minwax® Wood Finish™ Stain	Driftwood 2126	No Blend
Minwax	Minwax® Wood Finish™ Stain	Red Oak 215	No Blend
Minwax	Minwax® Wood Finish™ Stain	Fruitwood 241	No Blend
Minwax	Minwax® Wood Finish™ Stain	Pickled Oak 260	Similar to DriFast White stain wiped off well

# Bona® Drifast™ Stain Cross Reference Chart for DURA SEAL™ Penetrating Finish and Fast Dry Wood Stain

*Note: All matches were made using red oak that had a final screen cut of 80 grit. These blends should be used only as a starting point and further adjustments may be necessary to achieve the desired end result.*

MANUFACTURER	TYPE	NAME	BONA BLEND (DriFast Stain)
Duraseal	Dura Seal™ Penetrating Finish	Medium Brown 228	Medium Brown
Duraseal	Dura Seal™ Penetrating Finish	Antique Brown 216	Antique Brown
Duraseal	Dura Seal™ Penetrating Finish	Natural 200	1 Jacobean: 1 Provincial
Duraseal	Dura Seal™ Penetrating Finish	Chestnut 204	1.5 Natural: 1.5 Special Walnut: .33 Ebony
Duraseal	Dura Seal™ Penetrating Finish	Royal Mahogany 208	No Blend
Duraseal	Dura Seal™ Penetrating Finish	Neutral 210	No Blend
Duraseal	Dura Seal™ Penetrating Finish	Golden Brown 221	No Blend
Duraseal	Dura Seal™ Penetrating Finish	Ebony 231	No Blend
Duraseal	Dura Seal™ Penetrating Finish	Spice Brown 237	No Blend
Duraseal	Dura Seal™ Penetrating Finish	Rosewood 239	No Blend
Duraseal	Dura Seal™ Fast Dry Wood Stain	Medium Brown 228	Medium Brown
Duraseal	Dura Seal™ Fast Dry Wood Stain	Antique Brown 216	Antique Brown
Duraseal	Dura Seal™ Fast Dry Wood Stain	Golden Brown 221	No Blend
Duraseal	Dura Seal™ Fast Dry Wood Stain	Spice Brown 237	No Blend

## Bona DriFast Stain Blends

Bona	DS Stain	Neutral	3 Natural: 1 Golden
Bona	DS Stain	Spice	1 Jacobean: 4 Provincial
Bona	DriFast Stain Blend	Midnight Mahogany	3 Red Mahogany: 1 Ebony

Bona	DriFast Stain Blend	Light Ebony	3 Natural: 1 Ebony
Bona	DriFast Stain Blend	Autumn Gold	1 Golden: 1 Rosewood

## Bona DriFast Stain Blends Gray

Bona	DriFast Stain Blend	Light Gray	2 White: 1 Ebony
Bona	DriFast Stain Blend	Medium Gray	1 White: 1 Ebony
Bona	DriFast Stain Blend	Dark Gray	1 White: 2 Ebony

*Note: To achieve full color saturation, water-pop the floor prior to staining. Apply one even coat of warm water and allow it to dry overnight prior to applying the stain. Applying stain too soon over a water-popped floor can result in a blotchy, uneven stain color; extended dry times and finish adhesion failure.*

## Bona DriFast Stain Adding Courtines Paint/Universal Tints

If you are looking to achieve an even richer and darker color out of DriFast Stain (even more so than a water-popped floor will provide), you have two other options:

1. Bona CourtLines Sport Floor Paint can be mixed with Bona DriFast Stain.

OR

2. Universal Paint Tint\* can be mixed with Bona DriFast Stain.

\*Universal paint tint can be found at any local paint and/or hardware store.

Here are the guidelines if you choose to use one of the above methods to achieve a darker color of stain:

- Use a good quality, digital kitchen scale to accurately measure ratios of colorant to stain.
- Stir the Stain and the colorant (universal tint and/or CourtLines paint) thoroughly and batch multiple containers prior to application for larger jobs.
- Add no more than 8 ounces of colorant per gallon of Stain or 2 ounces colorant per quart.\*\*
- Let the Stain dry for a minimum of 24 hours, but no more than 48 hours. If the Stain dries for more than 48 hours, then Bona recommends lightly hand abrading the stain with a Bona Conditioning Pad prior to coating with a Bona urethane finish.
- Apply 2 – 3 coats of a Bona waterborne or oil-modified urethane directly on top of the Stain once dry.

*Note: If you choose to add more than the recommended ratio of paint or tint, dry*

*times will drastically increase and there is a great risk of adhesion failure with the top coats of urethane finish.*