



CHEVRON GREY

Warm brownish grey floor with occasional knots, cracks and fillings. A package contains an even split of left and right hand sided Chevron patterned boards. This product requires an, after installation, maintenance treatment using Kährs Satin Oil Matt.

PRODUCT DETAILS

| | |
|---------------------------|--------------------------|
| Article Number | 151XADEKWKW180 |
| Surface Treatment | Oil |
| Refining Treatment | Beveled 4-sided, Brushed |
| Dimensions | 72 3/4 x 12 x 19/32" |
| Weight per Package | 44 lbs |
| Area per Package | 21,96 sq ft |
| Area Per Board | 5,490 sq ft |

DETAIL DESCRIPTION

Naturally occurring wood colour variations allowed, from light to dark brown. The product includes medium sound and black knots. Knots may vary in size and numbers.

COLOUR CHANGE

Stained product - noticeable color change over time.

FACTS

| | |
|-----------------------------|--------------------|
| Wood Species | White Oak |
| Design | Pattern |
| Grading | Lively (Country) |
| Range | Kährs ID |
| Collection | Chevron Collection |
| Resandable | 2 times |
| Natural/Stained | Stained |
| Brinell Value | 3,7 |
| Joint | Tongue & Groove |
| Floor heating | Yes |
| Warranty | 30 years |
| Wear-layer material | Hardwood |
| Wear-layer thickness | 1/8" |
| Core material | Poplar |
| Thickness | 19/32" |
| Installation method | Glue-Down |
| Surface Color | Grey |

TECHNICAL PROPERTIES

| | | |
|-----------------------------------|-------------|-------------|
| Moisture content | EN13183 | 7%±2% |
| Minimum Mean Density kg/m³ | | >500 kg/m³ |
| Reaction To Fire | EN13501-1 | Dfl-s1 |
| Formaldehyde Emission | EN717-1 | E1 |
| Content PCP | CEN/TR14823 | ≤ 5 x 10-6n |
| Breaking Strength N/mm² | EN1533 | NPD |
| Thermal Conductivity | EN12664 | 0,14 W/mK |
| Thermal Resistance R-Value | | .11 (m2K/W) |
| Biological Durability | EN350-2 | Class 1 |
| CARB2 | | Compliant |

CERTIFICATES

